

High Temperature Deep Cycle GEL

SEHT210-6

The S.E Green SEHT deep cycle gel battery adopts the advanced developed nano gel electrolyte with super-C additive plus heavy duty plates design inside. It has a longer service life even deep cycle discharge use and can provide optimum and reliable service under extreme condition such as high temperature and frequent power failure, thus it is highly suited for tropical area in outdoor applications such as Telecom BTS stations and Off-grid PV system.

6V Voltage 210Ah Capacity Gel Technology Deep Cycle



COMPLIED STANDARDS

IEC 60896-21/22 JIS C8704
IEC61427 BS6290 part4
GB/T 19638 CE/ISO

GENERAL FEATURES


- Able to operate at 40-60°C
- Integrated design to ensure the best uniformity and reliability
- Longer life and higher stability under high temp. environment (no air-con needed)
- Super-C additives: Deep discharge recovery capability, 1600cycles @50%DOD

APPLICATIONS

- BTS Stations
- Solar & Wind energy system
- UPS system
- Telecom systems
- Wheel chair, Golf cart

DIMENSIONS & WEIGHT

Length (mm)	260±1
Width (mm)	180±1
Height (mm)	247±1
Total Height (mm)	252±1
Weight (kg)	29.6±3%



TECHNICAL SPECIFICATIONS

Nominal Voltage		6V (3 cells per unit)
Design Floating Life @25°C		20 Years
Nominal Capacity @25°C (20 hour rate@10.5A, 5.4V)		210Ah
Capacity @25°C	10hour rate (18.9A, 5.4V)	189Ah
	5 hour rate (33.4A, 5.25V)	167Ah
	1 hour rate (121.3A, 4.8V)	121.3Ah
Internal Resistance	Full Charged Battery@25°C	≤2.7mΩ
Ambient Temperature	Discharge	-25°C~60°C
	Charge	-25°C~60°C
	Storage	-25°C~60°C
Max.Discharge Current@25°C		630A(5s)
Capacity affected by Temperature (10 hour)	40°C	108%
	25°C	100%
	0°C	90%
	-15°C	70%
Self-Discharge@25°C per Month		3%
Charge (Constant Voltage) @25°C	Standby Use	Initial Charging Current Less than 42A Voltage 6.8-6.9V
	Cycle Use	Initial Charging Current Less than 42A Voltage 7.2-7.45V

BATTERY DISCHARGE TABEL

Discharge Constant Current per Cell (Amperes at 25°C)







F.V/Time	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h	100h
1.60V	328.0	195.2	138.6	121.3	74.0	52.0	35.3	23.3	20.8	11.3	2.52
1.65V	322.1	191.6	136.1	119.1	72.7	51.0	34.7	22.9	20.4	11.1	2.47
1.70V	316.1	188.1	133.6	116.9	71.3	50.1	34.1	22.5	20.0	10.9	2.42
1.75V	310.1	184.5	131.0	114.7	70.0	49.1	33.4	22.1	19.7	10.7	2.38
1.80V	298.2	177.5	126.0	110.3	67.3	47.3	32.1	21.2	18.9	10.5	2.33

Discharge Constant Power per Cell (Watts at 25°C)

F.V/Time	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h	100h
1.60V	631.4	375.8	266.8	233.5	142.5	100.1	68.0	44.9	40.0	21.8	4.85
1.65V	620.0	368.9	262.0	229.2	139.9	98.2	66.8	44.1	39.3	21.4	4.76
1.70V	608.5	362.1	257.1	225.0	137.3	96.4	65.6	43.3	38.6	21.0	4.67
1.75V	597.0	355.3	252.3	220.7	134.7	94.6	64.3	42.5	37.8	20.6	4.58
1.80V	574.0	341.6	242.6	212.2	129.6	91.0	61.9	40.8	36.4	20.2	4.49

Note: The above data are average values, and can be obtained within 3 charge/discharge cycles. These are not minimum values. Cell and battery designs/specifications are subject to modification without notice.

PERFORMANCE CHARACTERISTICS



BATTERY CONSTRUCTION

Component	Positive plate	Negative plate	Container & Cover	Safety valve	Terminal	Separator	Electrolyte	Pillar seal
Features	Thick high Sn low Ca grid with special paste	Balanced Pb-Ca grid for improved recombination efficiency	Fire resistant ABS (UL94-V0 optional)	Flame Si-Rubber and aging resistance	Female Copper Insert M8	Advanced PVC/AGM separator for high pressure cell design	Silicon Gel	Two layers epoxy resin seal